

---



---

**BITUMINOUS PAINT 11540**


---



---

<b>Description:</b>	<b>It is a special deep black, non poisonous modified bitumen paint.</b>
<b>Advantages:</b>	<ul style="list-style-type: none"> <li>• Very high adhesion.</li> <li>• Flow and easy to use.</li> <li>• Medium viscosity.</li> <li>• Very high spreading rate.</li> <li>• Very good water resistant finishing coat.</li> </ul>
<b>Fields of application:</b>	<ul style="list-style-type: none"> <li>• Used specially in water ballast, tanks.</li> </ul>
<b>Color</b>	Black.
<b>Finish</b>	Eggshell.
<b>Specific gravity:</b>	0.93 ± 0.05 gm / cm <sup>3</sup>
<b>Solid by volume:</b>	51 % (approx.).
<b>Theoretical spreading rate:</b>	13.8 m <sup>2</sup> / kg (at D.F.T 40 micron).
<b>Drying time:</b>	<ul style="list-style-type: none"> <li>• Surface: 3 - 4 hrs. (at 25°C &amp; 60% R.H.).</li> <li>• Complete: 24 hrs. (at 25°C &amp; 60% R.H.).</li> </ul>
<b>Time to recoat:</b>	<ul style="list-style-type: none"> <li>• Min.: 24 hrs (at 25°C &amp; 60% R.H.).</li> <li>• Max.: no limit.</li> </ul>
<b>Shelf life:</b>	12 months in its closed original cans at good stores in ideal conditions.
<b>Thinner:</b>	PACHIN 11500 or 10152.
<b>Method of application:</b>	<ul style="list-style-type: none"> <li>• By air spray: Volume of thinner: 1 - 5 % Nozzle orifice: 2 - 3 mm Nozzle pressure: 3 - 4 bar</li> <li>• By brush and roller: (for small areas) Volume of thinner: 5 - 10 %</li> </ul>
<b>Surface preparation:</b>	<ul style="list-style-type: none"> <li>• For new steel: Sand basting to Sa 2½ or steel brush to get clean surface condition.</li> <li>• For maintenance: remove dust, oil and grease by wet or dried abrasive or power tool cleaning.</li> </ul>