

## أنتى كاربونيشن ٨٩٥ - باكي شيلد

### الوصف

أنتى كاربونيشن ٨٩٥ من باكين ١٠٠٪ أكريليك مما يوفر حماية خارجية فائقة ومقاومة المياه ومقاومة الإتساع والتشقق. تكنولوجيا باكي شيلد ٨٩٥ المتقدمة تتواءم مع خواص الميكانيكية المميزة التي مكنته ان يجتاز العديد من الإختبارات مثل الإستطالة، النزغ، التشقق، نفاذية ثاني أكسيد الكربون وبخار الماء تلك الخواص المطلوبة لهذا النوع من الدهان.

### المميزات

تجعله مقاوم للتشقق  
مقاوم للإتساع  
مقاوم للكيمويات وخاصة ثاني أكسيد الكربون في الظروف القاسية

### طريقة التنفيذ

يجب أن يكون السطح سليماً، نظيفاً خالياً من الأتربة والزيوت والشحوم .... إلخ. كل الأجزاء الغير متماسكة يجب أن تزال، في حالة الأسطح المجيرة والترية يجب أن تزال بفرشاة ذات شعر خشن قوي.  
باكيشيلد ٨٩٥ يخفف بنسبة ٢٠٪ - ٢٥٪ بالماء  
ويستخدم كبرايمر لسد المسام للأسطح الجديدة..

## Anti Carbonation 895 - PachiShield

### Description:

Anti-Carbonation 895 is made entirely of acrylic and offers the best external protection against water, filth, and fracture resistance. The unique mechanics of PACHI Shield 895 combined with the state-of-the-art technology allow it to pass several tests, including elongation, stripping, cracking, and permeability to carbon dioxide and water vapor, which are essential qualities for this type of paint.

### Features :

Make it crack resistant  
anti-fouling  
Resistant to chemicals, especially carbon dioxide, in hard conditions

### Recommended Use :

The surface must be intact, clean and free from dust, oil and grease .... etc.  
All loose parts must be removed, in the case of silty surfaces and soils with a strong bristle brush.  
Pachi shield 895 Dilute 20% - 25% with water  
It is used as a primer to close pores for new surfaces.

### أدوات الاستخدام

الفرشاة / الرولة / مسدس الرش



### Application Tools

Brush / Roller / Spray gun

### زمن الجفاف

جفاف سطحي ٤-٥ ساعة  
جفاف كامل ٢٤ ساعة



### Drying Time

Surface dry 4 - 5 hr  
Through dry 24 hrs

### الصلاحية

٢٤ شهر



### Expiry

24 Months

### شروط التخزين

بعيداً عن أشعة الشمس



### Storage

Away from sunlight

### التخفيف

يخفف بنسبة ٢٠٪ - ٢٥٪ بالماء



### Dilution

Tap water up to 20 to 25%

### معدل الفرد

٤,٣ م<sup>٢</sup> / لتر عند ١٠٠ ميكرون  
سمك فيلم جاف.



### Coverage

from 2-3 m<sup>2</sup> / Ltr

### Technical Data :

### الخواص الفنية:

المظهر	المظهر	المظهر
Finish	مط	المظهر
Colors	أبيض وألوان حسب كارتة ألوان باكين	اللون
Solids by volume	43 % ± 2	نسبة المواد الصلبة بالحجم
Solids by weight	1.32 ± 0.05	نسبة المواد الصلبة بالوزن

أنتج طبقاً للمواصفات القياسية المصرية رقم ٢٠٢١/١٥٣٩  
This Product Produced under specification of PACHIN company according to ministerial decree no . 2021/1539

